

Solid Acrylic Resin PChem[®] BM55F

- Properties**
- 1, BM55F is a thermoplastic solid acrylic resin with good adhesion with substrates of unsaturated polyester and stainless steel especially at high temperature condition.
 - 2, BM55F is easily soluble in many organic solvents such as ketones, white spirit, esters, and aromatic hydrocarbons. It also has good compatibility with other film forming resins such as vinyl resins, and other acrylic resins.

Specifications	Properties	Value	Unit	Test methods
	Appearance	Pellets		
	Glass transition temperature (Tg)	68	°C	ASTM D-3418
	Molecular weight (Mw)	20,000	g/mol	ASTM D-3593
	Inherent viscosity (IV)	0.14		ASTM D-2857
	Acid value	<0.5	mgKOH/g	ISO-3682
	Moisture content	≤ 0.5	%	ISO-3251

- Packaging and storage**
- 1, Packed in composite paper bag with inner plastic bag, 25Kg net.
 - 2, Store in cool, dry and ventilated place where the fire and organic solvent are prohibited.
 - 3, Shelf life: 3 years, capable of further use after passing QC inspection.
 - 4, Transport as non-dangerous material.

Notes

The information contained on above data sheet is, to the best of our current knowledge, true and accurate. However, since the conditions of use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part. We disclaim all liabilities in connection with the use of information contained herein or otherwise. All risks of such nature are assumed by the user.