

Technical Data Sheet

MB-605 Page 1 of 1 June, 2014

Solid Acrylic Resin PChem® MB-605

- 1. MB-605 is an acrylic resin for use in solvent-based inks.
- 2. MB-605 provides excellent pigment wetting and dispersion characteristics.
- 3. MB-605 is soluble in esters, ketones, aromatic, glycol ethers and glycol ether acetates. MB-605 is very compatible with wide variety of other resins including acrylics, vinyl and nitrocellulose.

	Item	Value	Unit	Test method
Specifications	Appearance	Clear solid beads		
	Glass transition temperature (Tg)	60	°C	ASTM D-3418
	Molecular weight (Mw)	8,200	g/mol	ASTM D-3593
	Inherent viscosity (IV)	0.06		ASTM D-2857
	Acid value	53	mgKOH/g	ISO-3682
	Moisture content	≤ 1.0	%	ISO-3251

Packaging and storage

- 1. Packed in 25-kg paper bags.
- 2. Store in cool, dry and ventilated place where the fire and organic solvents are prohibited.
- 3. Shelf life: 3 years, capable of further use after passing QC inspection.
- 4, Transport as non-dangerous material.

Notes: The information contained on above data sheet is, to the best of our current knowledge, true and accurate. However, since the conditions of use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part. We disclaim all liabilities in connection with the use of information contained herein or otherwise. All risks of such nature are assumed by the user.

email: 9long@9long.com.cn